

iments for UV Measurem & Process Control




# AmeriWorx® Series



## MILLED VINYL TILE

Meets ANSI/ESD S20.20





**Spring Snow** 



Adirondack Ridge




Shenandoah Valley



**Big Sky Country** 




Rio Grande\*





Appalachian Spring\*






**AMERIWORX ROX** 

**Black Rock Canyon** 



**Grey Dolomite** 



Acadia Blue Rocks\*



Living Coral\*



Black Hills\*



**Great Plains\*** 



Morning Mist\*



Pearl\*



Blue Moraine\*

Lake Shore Boulder\*



Amethyst\*



Sedona Sandstone\*

\*non-stock, minimums apply

Conductive and Dissipative materials available.\*

Please note: Dissipative vinyl is a special order item.

All AmeriWorx tiles can be installed with StaticWorx Pressure-sensitive Adhesive

**Conductive and** dissipative materials available in all styles.

# Lifetime Conductivity Warranty

# AMERIWORX VINYL TILE

### BENEFITS

- Gap-Free Installation: Precision milled edges eliminate gaps in installation.
   High density resin eliminates tile shrinkage.
- Color runs through entire thickness of the tile so that deep scratches do not reveal a different color — helps hide scratches.
- Never requires wax: High density resin reduces maintenance, resists scuff marks and staining, and overall is easier to keep clean.
- Ideal for extreme duty manufacturing applications.
- Meets requirements for Buy Federal American as well as RoHS directive.

### INDOOR AIR QUALITY INFORMATION

California Department of Health CDPH/EHLB/Standard Method Version 1.1, 2010 (Emission testing method for CA Specification 01350)

- CALGreen, CA Code of Regulations Title 24, Part II, 2016, Sections 4.504.4/5.504.4.6: Resilient Flooring Systems
- ANSI/ASHRAE/USGBC/IES Standard 189.1-2017, Section 8.4.2.3: Floor Covering Materials
- USGBC LEED CI, NC, Schools, 2009, IEQ Credit 4.3: LEM
   Flooring Systems
- USGBC LEED for Healthcare, 2009 (Feb 2011), IEQ Credit 4: LEM, Group 3 Flooring
- Collaborative for High Performance Schools (CHPS) rating system, 2017 Criteria EQ2.2.3: Flooring Systems
- Green Guide for Healthcare, V2.2, 2007, EQ Credit 4.3:
   LEM Flooring Systems

### **SPECIFICATIONS**

**Composition:** Precision milled vinyl tile of high density resin with a conductive carbon matrix. Pre-consumer recycled content > 10%.

**Electrical Performance:** Lifetime Warranty

Free from defects in workmanship and materials:

Lifetime Warranty

Sizes: 12" x 12"

(24" x 24", 36" x 36" available as custom sizes)

Maintenance: No wax

Adhesive and Spread Rate: Covers approx. 180 - 220 sq. ft/gal

Gauge: 3.0 mm

**Grounding Material (Supplied with order):** One 2"x 24" copper

strip installed every 1,000 ft

**Trowel Sizes:** 1.6 x 1.6 mm (1/16"x 1/16") Square Notch with 1.6

mm (1/16") Flats



ESD Messaging Tiles Available



### **INDUSTRY TESTS**

Category	Test Method	Results
Critical Radiant flux CRF (W/cm²)	ASTM E-648	> 1.0 W/cm <sup>2</sup>
Chemical Resistance	ASTM F-925	Excellent (Acids, Alkalis, Household Chemicals)
Electrical Resistance	ASTM F-150	Point to Point & Point to Ground: 50,000 – 1,000,000 ohms Dissipative: 1,000,000 - < 1,000,000,000 ohms
<b>Electrostatic Propensity</b>	AATCC-134	<12 volts
Fire Resistance (Steiner Tunnel)	ASTM E-84	< 75 (Class 1)
<b>Electrically Conductive Floor Coverings</b>	ANSI/UL 779	Meets UL Standard
Floor Materials – Resistive Characterization of Materials	ANSI/ESD.S7.1-2013  Conductive: $< 1.0 \times 10^6$ Dissipative: $\ge 1.0 \times 10^6$ and $< 1.0 \times 10^9$	Surpasses recommended standards of ANSI/ESD S20.20-2014
Floor Materials and Footwear-Resistance Measurement in Combination with a Person	ANSI/ESD STM97.1-2015 < 3.5 X 10 <sup>7</sup>	Surpasses recommended standards of ANSI/ESD S20.20-2014
Floor Materials and Footwear- Voltage Measurement in Combination with a Person	ANSI/ESD STM97.2-2016 <25 volts with conductive footwear	Surpasses recommended standards of ANSI/ESD S20.20-2014
Life Safety Code	NFPA 101	Passes
Smoke Density	ASTM E-662	≤ 450
Solid Vinyl Floor Covering Materials	ASTM F-1700	Conforms
Standard for Health Care Facilities	NFPA 99	Passes
Static Decay, Method 4046 at 15% RH	ASTM F-101C	5000 – 0 Volts in <0.01 sec.
Static Load	ASTM F-970	< 0.001" RI @ 250 psi (1.125" diameter foot) 0.005" RI @ 2,500 psi (0.5" diameter foot)

