

PRODUCT DESCRIPTION

A new, state-of-the-art floor maintenance finish with inherent static-dissipating properties, specifically formulated for application in computer rooms, electronic assembly areas, telephone sub-stations, or any other area where positive elimination of static electricity is a prime consideration. The unique static-dissipating ingredient is actively linked to the chemical structure of the polymer system, preventing wash-out, or leaching of the static dissipating properties. Easy maintenance, good gloss, and durability are additional assets of this high-tech anti-static finish.

APPLICATION & MAINTENANCE

Best results are obtained when StaticWorx CoatZF static-dissipative floor finish is applied to surfaces which are 60° F. or warmer with relative humidity between 40 – 65%.

1. Remove old finish or wax with StaticWorx EcoScrub Degreaser (stripper). Follow directions on stripper label for application.
2. On initial application, for optimum appearance apply three to five coats of finish. No more than 3 coats should be applied in an 8 hour period.
3. Apply thin, even coats, allowing the finish to dry between coats. Depending on humidity and temperature, dry for 30 – 45 minutes before applying the next coat.

To recoat existing ScrubWorx finish:

1. Vacuum the floor to remove any loose dirt or dust.
2. Wash the floor with StaticWorx ScrubWorx 20.20 to remove dirt and soil.
3. Apply thin, even coats, allowing the finish to dry for approximately 30 minutes before resumption of foot traffic.

The necessary frequency of stripping and refinishing may vary depending on environmental conditions within a particular facility. Field experience indicates that monthly refinishing generally provides optimum results.

A routine maintenance program will provide the most satisfactory gloss retention and wear characteristics in any floor coating. Sweep the floor daily with an untreated mop to remove abrasive loose dirt and sand. Floors should be damp-mopped with StaticWorx ScrubWorx 20.20 regularly, as needed, to remove soil, salt, and film deposits which can degrade the coatings' conductive properties and gloss.

PRODUCT SPECIFICATIONS

Nonvolatile Solids:	18 + 0.6%
Total Active:	22%
Resistivity-ASTM D257:	10 ⁸⁻⁹ ohms ² max/cm ² @ 40% relative humidity
Static Dissipation:	0.02 second
pH:	8.4 – 9.0
Gloss 600:	80+ @ 3 coats
Color:	Translucent white
Weight per Gallon:	8.55 - 8.8
Slip Resistance (ASTM):	0.52 minimum
Stability:	1 year minimum at room temperature
Freeze/Thaw Stability:	3 cycles minimum
Drying Time:	30 – 45 minutes
Water Resistance:	Good
Gallon Coverage (Feet²):	1500 - 2000 ft ²
Removability (Gardner):	75 cycles maximum

SAFETY INFORMATION

Health: 1

Flammability: 0

Reactivity: 0

Personal Protection: B

This material is not a hazardous mixture, as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested drink milk, water, fruit juice, and induce vomiting with oil of ipecac. In the event of eye contact flush area with water for 15 minutes. Contact a Physician. For detailed information consult MSDS sheet.

TECHNICAL INFORMATION

Maintenance Questions? Call StaticWorx at (617) 923-2000.